

## SYSTEM DATA SHEET

# Sikafloor® MultiDur ET-14 ECC

### TEXTURED UNICOLOUR EPOXY FLOOR COVERING OVER EPOXY HYBRID SCREED

### **DESCRIPTION**

Sikafloor® MultiDur ET-14 ECC is a coloured rigid epoxy floor covering with textured properties based on epoxy resins for industrial floors on damp substrates.

#### USES

Sikafloor® MultiDur ET-14 ECC may only be used by experienced professionals.

- for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- for multi-storey and underground car parks, maintenance hangars and for wet process areas, e.g. beverage and food industry.
- for areas where slip resistance and easy cleanability is required

### **CHARACTERISTICS / ADVANTAGES**

- Good mechanical resistance
- Good chemical resistance
- Medium thermal shock resistance
- Fast and easy application
- Thermal expansion properties similar to concrete
- Excellent bond to green or hardened concrete whether damp or dry
- Excellent early and final mechanical strengths
- Excellent resistance to water and oils
- For internal use
- Contains no solvents
- Will not corrode reinforcement steel

### PRODUCT INFORMATION


Packaging	Please refer to the individual Product Data Sheet
Shelf Life	Please refer to the individual Product Data Sheet

SYSTEM DATA SHEET Sikafloor® MultiDur ET-14 ECC November 2018, Version 02.01 020811900000000003

### **SYSTEM INFORMATION**

### **System Structure**

### Sikafloor® MultiDur ET-14 ECC



Layer	Product
1.Primer	1–2 coats x Sikafloor®-80 EpoCem®
	Primer
2.Levelling screed	Sikafloor®-81 EpoCem® New HC
3.Top coat	1–2 layers × Sikafloor®-264 HC + Ex-
	tender-T

Composition	Ероху
Appearance	Textured, gloss finish
Colour	Almost unlimited choice of colour shades.
Nominal Thickness	~2–4mm

### **TECHNICAL INFORMATION**

Shore D Hardness	~76 (7 days / +23 °C)	(DIN 53 505)	
Tensile Adhesion Strength	> 1.5 N/mm² (failure in concr	ete) (ISO 4624)	
Chemical Resistance	Please refer to the chemical resistance of Sikafloor®- 264 HC		
Temperature Resistance	Exposure*	Dry heat	
	Permanent	+50 °C	
	Short-term max. 7 d	+80 °C	
	Short-term max. 12 h	+100 °C	
	Short-term moist/wet heat* al (steam cleaning etc.) *No simultaneous chemical a	up to +80 °C where exposure is only occasion- and mechanical exposure.	

### **APPLICATION INFORMATION**

Consumption	Sikafloor® MultiDur E	Sikafloor® MultiDur ET-14 ECC			
	Coating System	Product	Consumption		
	1. Primer	1–2 coats × Sikafloor®- 80 EpoCem® Primer	~0.25–0.40 kg/m²		
	2.Levelling screed	1 × Sikafloor®-81 Epo- Cem® New HC	~2.25 kg/m²/mm (For TMB minimum 2 mm thick)		
	3.Top coat	1–2 layer x Sikafloor®- 264 HC + 1–2 % pbw Extender-T	~0.5–0.8 kg/m² per layer		

SYSTEM DATA SHEET
Sikafloor® MultiDur ET-14 ECC
November 2018, Version 02.01
02081190000000003



Product Temperature	Please refer to the	Please refer to the individual Product Data Sheet				
Ambient Air Temperature	+10 °C min. / +3	+10 °C min. / +30 °C max.				
Relative Air Humidity	80 % r.h. max.	80 % r.h. max.				
Dew Point	Beware of condensation! The substrate and uncured floor temperature must be at least 3 °C above the dew point to reduce the risk of condensation or blooming on the floor finish.					
Substrate Temperature	+10 °C min. / +3	+10 °C min. / +30 °C max.				
Substrate Moisture Content	though the syste hours), it is advis to occur in order	Can be applied on green or damp concrete, without any standing water. Although the system can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early shrinkage of concrete to occur in order to prevent concrete shrinkage cracks from appearing on the screed surface.				
Pot Life	Please refer to the	he indivi	dual Produ	ıct Data Sheet		
Waiting Time / Overcoating	Before applying Primer allow:	Before applying Sikafloor®-81 EpoCem® New HC on Sikafloor®-80 EpoCem® Primer allow:				
	Substrate temperature					
		erature		1	Maximum	
	+10 °C	erature	12 hours	1	24 hours	
	+10 °C +20 °C	erature	12 hours 6 hours	1	24 hours 12 hours	
	+10 °C	erature	12 hours	1	24 hours	
	+10 °C +20 °C +30 °C	ooCem® I	12 hours 6 hours 4 hours New HC ca	n be overcoate	24 hours 12 hours	
	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su	oCem® I	12 hours 6 hours 4 hours New HC ca	n be overcoate	24 hours 12 hours 6 hours ed with vapour tight coat-	
	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than	oCem® I	12 hours 6 hours 4 hours New HC ca	n be overcoate ls below 4 %!	24 hours 12 hours 6 hours ed with vapour tight coat-	
	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than Substrate Temp	oCem® I	12 hours 6 hours 4 hours New HC ca	n be overcoate ls below 4 %! Waiting Tir	24 hours 12 hours 6 hours ed with vapour tight coat-	
	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than Substrate Temp +10 °C	oCem® I	12 hours 6 hours 4 hours New HC ca	n be overcoate s below 4 %!  Waiting Tin 2 days	24 hours 12 hours 6 hours ed with vapour tight coat-	
Applied Product Ready for Use	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than Substrate Temp +10 °C +20 °C	ooCem® I urface hi : erature	12 hours 6 hours 4 hours New HC ca	n be overcoate s below 4 %! Waiting Tin 2 days 1 day	24 hours 12 hours 6 hours ed with vapour tight coat-	
Applied Product Ready for Use	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than Substrate Temp +10 °C +20 °C +30 °C	ooCem® I urface hi : erature	12 hours 6 hours 4 hours New HC ca umidity fal	n be overcoate ls below 4 %!  Waiting Tin 2 days 1 day 1 day	24 hours 12 hours 6 hours ed with vapour tight coat-	
Applied Product Ready for Use	+10 °C +20 °C +30 °C Sikafloor®-81 Ep ings when the su Not earlier than Substrate Temp +10 °C +20 °C +30 °C  Temperature	ooCem® lurface hu: erature	12 hours 6 hours 4 hours New HC ca umidity fal	n be overcoate s below 4 %!  Waiting Tine 2 days 1 day 1 day  Light traffic	24 hours 12 hours 6 hours ed with vapour tight coat-	

### **MAINTENANCE**

### **CLEANING**

Refer to the Method Statement Sikafloor®-Cleaning Regime

### **FURTHER DOCUMENTS**

- Sika® Method Statement Mixing & Applications of Flooring systems
- Sika® Method Statement Evaluation and Preparation of Surfaces for Flooring systems

### **IMPORTANT CONSIDERATIONS**

- Always ensure good ventilation when using Sikafloor® MultiDur ET-14 ECC in a confined space to remove excess moisture.
- Freshly applied Sikafloor® MultiDur ET-14 ECC must be protected from damp, condensation and water for at least 24 hours.
- Prevent premature drying by protecting from strong wind and do not expose to direct sun light while fresh.

- Applications under extreme conditions (high temperature and low humidity) which can cause fast drying of the products must be avoided as the product does not allow the use of curing compounds.
- Static cracks: Prefill and level with Sikadur® or Sikafloor® epoxy resin
- For exact colour matching, ensure the Sikafloor®-264
   HC in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.



#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai Negeri Sembilan D.K., Malaysia Phone: +606-7991762 Fax: +606-7991980 e-mail: info@my.sika.com Website: www.sika.com.mv





SYSTEM DATA SHEET Sikafloor® MultiDur ET-14 ECC November 2018, Version 02.01 0208119000000000003

