



BUILDING TRUST



PRODUCT DATA SHEET

Davco ExtraGloss Sealer 139

Protective sealer and coating

DESCRIPTION

Davco ExtraGloss Sealer 139 is used for protecting slates, bricks, concrete, paving tiles, terracotta tiles, cultured stone from staining, efflorescence and for easy maintenance. It is a penetrating sealer that brightens up the colours of the material giving the surface a fine semi-lustrous finish.

USES

- Slates
- Bricks
- Concrete
- Paving tiles
- Terracotta tiles

CHARACTERISTICS / ADVANTAGES

- Protects surface from elements of water, dirt, oil or fungus
- Resistant to most household chemical
- Gives a 'glossy' when applied to most surfaces
- Easy to clean and maintain
- Highly resistant to foot traffic

PRODUCT INFORMATION

Packaging	5 L
Appearance / Colour	Clear, yellowish liquid
Shelf life	12 months from date of production
Storage conditions	Store properly in original, unopened and undamaged packaging in cool, dry conditions.

APPLICATION INFORMATION

Consumption	~15–20 m ² /l per coat depending on surface porosity and roughness
-------------	---

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

age and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, stor-

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

All surfaces must be structurally sound, dry, clean and free from movement, oil, grease, wax, curing compound and any other loose or contaminating materials.

Wait for 24 hours after washing or rain. Application on damp or wet surface will cause hazy white appearance and a loss of adhesion of the coating. Do not apply if there is rain.

MIXING

Do not shake, stir slowly. Avoid whipping air into Davco ExtraGloss Sealer 139.

APPLICATION

Apply Davco ExtraGloss Sealer 139 with brush or roller. Apply minimum 2 coats by allowing 30 minutes to 1 hour drying in between coat. For added protection apply 3 coats. Stone porous surfaces may require additional coat after full cure. Test a small area to determine suitability of sealer on the stone surface. Allow Davco ExtraGloss Sealer 139 to cure for 4–5 days without scrubbing or washing. If required, use a vacuum or damp mop for cleaning during the curing period.

It is user's responsibility to ensure suitability of a sealer before actual application as the characteristics of stone may differ from different origin.

CLEANING OF EQUIPMENT

Davco ExtraGloss Sealer 139 and tools can be cleaned with Sika Thinner C immediately after use while it is still wet.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,
71800 Nilai, Negeri Sembilan D.K.
Malaysia
Phone: +606-7991762
e-mail: info@my.sika.com
Website: www.sika.com.my



Product Data Sheet

Davco ExtraGloss Sealer 139
August 2021, Version 01.01
02189010000000003

DavcoExtraGlossSealer139-en-MYDAVCO-(08-2021)-1-1.pdf