

PRODUCT DATA SHEET

SikaFiber® Force PP-65/RAD65s

POLYOLEFIN MACRO-SYNTHETIC FIBRES FOR REINFORCED SHOTCRETE AND CONCRETE

DESCRIPTION

SikaFiber® Force PP-65/RAD65s is a macro structural synthetic polypropylene fibre. These fibres show very defined ductile behavior characteristics with excellent performance levels in shotcrete.

USES

- Fibrecrete/shotcrete
- Ground supported slabs
- Precast
- Sea defence
- Airport & pavements
- Slope stabilisation

CHARACTERISTICS / ADVANTAGES

- Uniquely designed and packaged allowing it to be evenly dispersed ensuring no balling or pumping problems will occur
- Non-magnetic, rustproof and alkali proof
- Less balling effect for difficult mixes
- No site waste or disposal issues
- Saves time and storage space in comparison to traditional mesh
- Environmentally friendly recycled packaging.

PRODUCT INFORMATION

Composition	Virgin polyolefin polymer	
Packaging	5 Kg boxes- fibres wrapped in water soluble plastic pucks (Parallel Packed) in biodegradable boxes	
Appearance / Colour	Embossed plastic fiber	
Shelf Life	N/A	
Storage Conditions	Store in dry conditions, protected from the weather	
Density	0.92 g/cm ³	
Dimensions	Length	65 mm
	Mean thickness	0.34 mm
Melting Point	170 °C	

TECHNICAL INFORMATION

Water Absorption	Nil
Tensile Strength	550+ MPa
Resistance to Alkalinity	Excellent

APPLICATION INFORMATION

Recommended Dosage	5–9 kg/m ³
Compatibility	SikaFiber® Force PP-65/RAD65s macro-synthetic fibers are compatible with all concrete admixtures and performance-enhancing chemicals. SikaFiber® Force PP-65/RAD65s macro-synthetic fibers are compatible with all concrete admixtures and performance-enhancing chemicals.

APPLICATION INSTRUCTIONS

DISPENSING

Entire package can be thrown into the mix allowing for easy handling whilst leaving no waste on site. Allow 3 to 5 minutes at mixing speed for fibers to disperse evenly throughout matrix. Can be added to the mix at any stage during batching.

FURTHER DOCUMENTS

Specification clause

Fibers for concrete shall be SikaFiber® Force PP-65/RAD65s polyolefin high performance macro-synthetic fibre conforming to EN 14889-2:2006 Class II and manufactured specifically for the reinforcement of concrete. SikaFiber® Force PP-65/RAD65s macro-synthetic fibres shall be mixed at the batch plant, at the recommended rate of 5–9 kg per cubic metre, and mixed for sufficient time (minimum 5 minutes) to ensure uniform distribution of the fibers throughout the concrete mix.

IMPORTANT CONSIDERATIONS

The addition of SikaFiber® Force PP-65/RAD65s can cause a reduction of the concrete consistency. We recommend correcting this loss not by adding water, but by adjusting the mix to the required workability, with a suitable dosage of Sika® high-range water reducing admixture (Sika® ViscoCrete®).

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

No special handling is required with SikaFiber® Force PP-65/RAD65s macro-synthetic fibres.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800
Nilai
Negeri Sembilan D.K., Malaysia
Phone: +606-7991762
Fax: +606-7991980
e-mail: info@my.sika.com



Product Data Sheet
SikaFiber® Force PP-65/RAD65s
January 2020, Version 01.01
021408021000000075

SikaFiberForcePP-65RAD65s-en-MY-(01-2020)-1-1.pdf