

## PRODUCT DATA SHEET

# Sikalastic® M 689

(formerly MSeal M 689)

A highly elastic, ultra-fast curing, spray applied 100 % polyurea membrane for use in waterproofing applications

### DESCRIPTION

Sikalastic® M 689 is a 2- part, solvent-free, pure polyurea, hot spray applied, elastic, very fast curing, waterproofing and protection membrane. The fast curing allows an immediate return-to-service time and the spray application allows fast coverage of the substrate.

### USES

Sikalastic® M 689 may only be used by experienced professionals.

It is used in a variety of waterproofing applications, especially where a high degree of chemical and mechanical resistance is required.

This includes:

- Waste water treatment plants (urban and industrial), both in the inflow and outflow areas.
- Sewage effluent pipelines.
- Steel and concrete pipes.
- Secondary containment bunds in chemical and petro-chemical industries.

Additionally, Sikalastic® M 689 can be applied on:

- Flat and architectural roofs.
- Horizontal and vertical substrates.
- Internal and external areas.
- Concrete, cementitious mortar or steel substrates.
- Reinforced concrete to protect it against carbonation, chloride induced corrosion or chemical attack in industrial environments.

Contact your local Sika representative regarding any application required not mentioned here.

### CHARACTERISTICS / ADVANTAGES

- Low emission (conform to AgBB)
- Low viscosity
- Excellent bond to substrate
- High moisture tolerance
- ultra-fast curing
- Monolithic membrane
- Excellent chemical resistance
- Waterproof and resistant to standing water
- Fully bonded to substrate
- High water vapour permeability
- High resistance to carbon dioxide diffusion
- High abrasion and impact resistance
- High elasticity and crack bridging capability
- Thermoset – does not soften at high temperatures

### APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating

## PRODUCT INFORMATION

Product Declaration	EN 1504-2: Surface protection product for concrete - Coating		
Composition	Pure polyurea		
Packaging	Part A (Polyamine)	200 kg drums	~203 litres
	Part B (Isocyanate)	225 kg drums	~203 litres
Shelf Life	Part A: 12 months from date of production Part B: 9 months from date of production		
Storage Conditions	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +15 °C and +25 °C. Do not expose to direct sunlight. Always refer to packaging.		
Colour	Sikalastic® M 689 is available in the following colour combination: <b>Part A:</b> <ul style="list-style-type: none"> <li>▪ Dark grey close to RAL 7043,</li> <li>▪ Medium grey close to RAL 7042,</li> <li>▪ Light grey close to RAL 7035</li> <li>▪ Black</li> <li>▪ Colourless (to be coloured with Sika authorized pigment paste by approx. 3–5 %. Stir well before use!)</li> </ul> <b>Part B:</b> Unpigmented		
Density	Part A	~1.01 kg/l	
	Part B	~1.11 kg/l	
	Mix	~1.10 kg/l	
Values at +20 °C			
Viscosity	Temperature	Part A	Part B
	+25 °C	220 mPas	800 mPas

## TECHNICAL INFORMATION

Shore A Hardness	> 90	
Shore D Hardness	> 40	
Mechanical Resistance	< 150 mg	H22 / 1000 g / 1000 cy
Resistance to Impact	> 20 Nm (Class III)	(EN ISO 6272/2)
Tensile Strength	> 20 N/mm <sup>2</sup>	
Elongation at Break	~425 %	(DIN 53504)
Crack Bridging Ability	Class A5	Static
	Class B4.2 (-20 °C)	Dynamic
Tear Strength	58 N/mm <sup>2</sup>	(DIN 53515)
Skid / Slip Resistance	63 (Class II)	Dry
	30	Wet
Service Temperature	-30 °C min. / +130 °C max.	dry
	0 °C min. / +80 °C max.	high moisture, but not wet
	0 °C min. / +55 °C max.	wet
Capillary Absorption	0.002 kg/m <sup>2</sup> /h <sup>0.5</sup>	(DIN EN 1062-3)
Permeability to Water Vapour	Sd value H <sub>2</sub> O < 5m	

<b>Permeability to Carbon Dioxide</b>	Sd value CO <sub>2</sub> > 120m
<b>Chemical Resistance</b>	Resistant to many chemicals. Contact Sika Technical Services for additional information.
<b>Behaviour after Artificial Weathering</b>	no changes (EN 1062-11)
<b>Reaction to Fire</b>	Cfl-s1 (DIN EN 13501-1)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Part A : Part B = 1 : 1 (by volume)
<b>Consumption</b>	~1.10 kg/m <sup>2</sup> /mm
<b>Layer Thickness</b>	> 2 mm
<b>Product Temperature</b>	> +70 °C
<b>Ambient Air Temperature</b>	+5 °C min. / +35 °C max.
<b>Relative Air Humidity</b>	< 90 %
<b>Dew Point</b>	Beware of condensation. The substrate and uncured applied floor material must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.
<b>Substrate Temperature</b>	+5 °C min. / +35 °C max.
<b>Substrate Moisture Content</b>	< 4 %
<b>Curing Time</b>	Final cure ~24 hours at +20 °C Time is approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.
<b>Gel Time</b>	~8 seconds at +20 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Sika Method Statement: Sikalastic® M 689

## IMPORTANT CONSIDERATIONS

Reference must be made to the Sika® Method Statement: Sikalastic® M 689

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### EQUIPMENT

Reference must be made to the Sika® Method Statement: Sikalastic® M 689

### SUBSTRATE QUALITY

Reference must be made to the Sika® Method Statement: Sikalastic® M 689

### SUBSTRATE PREPARATION

Reference must be made to the Sika® Method Statement: Sikalastic® M 689

### MIXING

Reference must be made to the Sika® Method Statement: Sikalastic® M 689

Note: Both components must be heated up to +70 °C. The accuracy of mixing and dosage must be controlled regularly with the spray equipment. Thoroughly stir Part A (Amine) using a drum stirrer until a uniform consistent colour is obtained.

## APPLICATION

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions. Prior to application, confirm substrate moisture content, relative air humidity, dew point, substrate, air and product temperatures. Reference must be made to the Sika Method Statement: Sikalastic® M 689

## CLEANING OF TOOLS

Clean all tools with Thinner C immediately after use. The application equipment must be cleaned and filled with Mesamoll. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,  
71800 Nilai, Negeri Sembilan D.K.  
Malaysia  
Phone: +606-7991762  
e-mail: info@my.sika.com  
Website: www.sika.com.my



### Product Data Sheet

Sikalastic® M 689  
September 2024, Version 02.01  
02070600000002018

SikalasticM689-en-MY-(09-2024)-2-1.pdf