

## PRODUCT DATA SHEET

# SikaWall®-192 Finish EM

High performance, cementitious finish skimcoat for internal wall

### DESCRIPTION

Previously known as Davco Plaster Finish Skim Coat (Internal). SikaWall®-192 Finish EM is a one component cementitious fine finishing coat for skimming on wall and ceilings. It's smooth finishing and good adhesion is suitable for internal application.

### USES

SikaWall®-192 Finish EM is a fast and economical way to patch fine surface imperfections such as pinholes and hairline cracks.

### CHARACTERISTICS / ADVANTAGES

- Provide a good fine surface finish on walls, ceilings, etc.
- Higher durability and flexibility
- Quick drying and easy to apply
- Thickness of the plaster can be varied to minimise wastage
- Non-combustible
- Non-cracking when applied at correct thickness and properly cured
- Easy to mix – just add water
- Good adhesion
- Can be applied by spraying

### PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	<ul style="list-style-type: none"> <li>▪ Grey powder</li> <li>▪ White powder</li> </ul>
Shelf Life	6 months from the date of production
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight, rain and water.

### TECHNICAL INFORMATION

Tensile Adhesion Strength	≥ 0.4 N/mm <sup>2</sup>	(EN 1015-12)
---------------------------	-------------------------	--------------

### APPLICATION INFORMATION

Mixing Ratio	9–9.75 L water per 25 kg bag
Consumption	1.1–1.2 kg/m <sup>2</sup> /mm * Dry powder * This may only serve as a guideline. It is highly recommended to carry-out trials on site to determine the actual coverage.
Layer Thickness	1.0–3.0 mm
Fresh Mortar Density	1.6–1.9 kg/l

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- Do not use SikaWall®-192 Finish EM on painted or gypsum surfaces.
- Applications of SikaWall®-192 Finish EM which are too thin can result in a chalky or dusty finish that is unsuitable for painting or subsequent applications.
- Applications of SikaWall®-192 Finish EM on very porous or dry substrates can result in a chalky or dusty finish that is unsuitable for painting or subsequent applications.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be sound, clean, dry and free of all contaminants e.g. dirt, oils, grease, coatings, surface treatments, etc. If in doubt, apply a test area first. Dry concrete, render or SikaWall® surfaces must be prewetted before application.

### MIXING

SikaWall®-192 Finish EM must be mixed with clean water at the site using a power drill whisk. Pour the required water into a suitable container then add SikaWall®-192 Finish EM while stirring continuously until a smooth consistency is achieved. Allow mixture to stand for a few minutes. Mix again and the plaster is ready for use.

## APPLICATION METHOD / TOOLS

SikaWall®-192 Finish EM is applied either by hand with a steel trowel or spatula. The coat is then levelled off to a smooth surface with a steel trowel. Ensure that the applied coat has hardened before application of subsequent coats.

## CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened or cured material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,  
71800 Nilai, Negeri Sembilan D.K.  
Malaysia  
Phone: +606-7991762  
e-mail: info@my.sika.com  
Website: www.sika.com.my



Product Data Sheet  
SikaWall®-192 Finish EM  
December 2024, Version 02.01  
021840101000000056

SikaWall-192FinishEM-en-MY-(12-2024)-2-1.pdf