

PRODUCT DATA SHEET

SikaGrout® GP

GENERAL PURPOSE, PUMPABLE, SHRINKAGE-COMPENSATED CEMENTITIOUS GROUT

DESCRIPTION

SikaGrout® GP is a pumpable, shrinkage-compensated, flowable cementitious grout with extended working time to suit local ambient temperatures.

USES

SikaGrout® GP is a general purpose grout suitable for the following applications:

- Grouting works for machine foundations, anchor bolts, bridge bearings, etc.
- Filling of cavities, gaps, recesses, etc.
- Concrete repairs (pre-packed grouting)

For precision grouting, SikaGrout®-215 is recommended.

CHARACTERISTICS / ADVANTAGES

- Easy to mix and apply
- Flowable consistency (according to mix)
- Rapid strength development
- Non-corrosive
- Non-toxic
- Iron and chloride free
- Shrinkage-compensated
- Good pumping properties

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Grey premixed powder
Shelf Life	6 months from the date of production
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +10 °C and +35 °C. Protect from direct sunlight.
Density	~2.2 kg/l (depending on consistency and temperature)
Maximum Grain Size	2 mm

TECHNICAL INFORMATION

Compressive Strength	Flowable consistency		
	24 hours	> 20 N/mm ²	(ASTM C 109)
	7 days	> 45 N/mm ²	
	28 days	> 55 N/mm ²	

Expansion	Flowable consistency ≥ 0.5% at 24 hours	(ASTM C 940)
Reaction to Fire	Fire rating, Classified A1 SikaGrout® GP will not contribute in any state of the fire including the fully developed fire.	(EN 13501-1)

APPLICATION INFORMATION

Mixing Ratio	Consistency	Water (L) per 25 kg of grout
	Flowable	4.3–4.5
	Pourable	3.6–4.0

These mix ratios are a guide and preliminary trials at local temperatures / humidity conditions are recommended.

Yield	Flowable consistency		
	SikaGrout® GP	Water	Volume Mortar
	1.82 kg	0.33 L	1 L
	25 kg	4.5 L	13.7 L
	73 x 25 kg bag	330 L	1 m ³
	Pourable consistency		
	SikaGrout® GP	Water	Volume Mortar
	1.94 kg	0.29 L	1 L
	25 kg	3.75 L	12.9 L
	78 x 25 kg bag	290 L	1 m ³

Layer Thickness 10 mm min. / 50 mm max. per pour (neat grout)

Flowability **Flowable consistency**
≥ 270 mm (at 3 mins) (EN 1015-3)

Ambient Air Temperature +10 °C min. / +40 °C max.

Substrate Temperature +10 °C min. / +40 °C max.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate should be prepared by suitable mechanical preparation techniques such as high pressure water, breakers, grit blasting, scabblers, etc. All absorbent surfaces must be well saturated with clean water, but free of any surface water or puddles prior to the application of SikaGrout® GP.

Concrete, mortar and stone

Surfaces must be sound, clean, free from frost, oils, grease, standing water and all loosely adhering particles and other surface contaminants.

Metal surfaces (iron and steel)

Surfaces should be clean, free from scale, rust, oil and grease.

MIXING

Place about 70–80 % of the premeasured clean water (depending on consistency required – refer to “Mix Ratio”) into a clean container and gradually add the whole bag of SikaGrout® GP into it while continuously mixing. Add the remaining water until the desired consistency is obtained.

Mix for 2–3 minutes with a low speed drill attached to a helical paddle mixer, eg. WK140HF from Collomix (500 rpm max.).

APPLICATION

After mixing, stir lightly with a spatula for a few seconds to release any entrapped air. The grout is then poured immediately into the prepared formwork. When carrying out baseplate grouting, ensure sufficient pressure head is maintained for uninterrupted mortar flow. For formwork repair, the prepared formwork must be firmly in place and kept watertight. When placing grout over a large area, it is important to maintain a continuous flow throughout. Work sequence must be properly organised to ensure an uninterrupted flow. In large areas, SikaGrout® GP may be pumped using heavy duty diaphragm pumps. Screw feed and piston pumps may also be used.

Specific Areas of Application

Grouting under baseplate	pourable consistency
Formwork grouting - pouring method	flowable / pourable consistency
Formwork grouting - pre-packed method	flowable consistency
Grouting anchor bolts	stiff consistency

Grouting large volumes

For sections thicker than 50 mm, it is necessary to fill SikaGrout® GP with graded 10 mm silt free aggregates to minimise temperature rise generated during the curing stage. The quantity of aggregates should not exceed 1 part aggregates to 1 part SikaGrout® GP by weight. For such mixes, a conventional concrete mixer and pump may be used. To further ensure that air entrapped during mixing is allowed to fully escape, it may be necessary to make breather holes. Use steel rods or chains to assist the flow of grout where necessary. Preliminary trials are recommended.

CURING TREATMENT

When formwork type repair is used, leave the formwork in place for at least 3 days. Upon removal of the formwork, cure the exposed surfaces immediately with Antisol® curing compound or use other approved curing methods.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened or cured material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

At temperatures +20 °C and below, setting time and strength development will be slower. Non-shrink grout contains additives which expand either during the plastic stage and / or the hardening stage to compensate for the shrinkage of the cementitious matrix. However, this 'non-shrink' property will be effective only if the material is not subjected to water loss. This is confirmed by a note in the ASTM C 1107 Standard Specification for packaged dry, hydraulic cement grout (non-shrinkable), which clarifies the behaviour of the non-shrink grout when subjected to some drying: "Note 1: Since all conditions of use cannot be anticipated, this specification requires non-shrink grout to exhibit no shrinkage when tested in a laboratory controlled moist-cured environment, and requires only the reporting of the observed height change, usually shrinkage, when test specimens are subject to some degree of drying."

Sika Kimia Sdn. Bhd.
Lot 689, Nilai Industrial Estate, 71800 Nilai
Negeri Sembilan D.K., Malaysia
Phone: +606-7991762
Fax: +606-7991980
e-mail: info@my.sika.com
Website: www.sika.com.my



Product Data Sheet
SikaGrout® GP
August 2017, Version 01.01
020201010010000085

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaGroutGP-en-MY-(08-2017)-1-1.pdf