

PRODUCT DATA SHEET

Sikalastic®-827 HT

MODIFIED HOT- MELT ADHESIVE

DESCRIPTION

Sikalastic®-827 HT is a modified, expanding, hot-melt adhesive used as part of the bridge deck waterproofing system underneath mastic asphalt, stone mastic asphalt and asphalt concrete.

USES

Sikalastic®-827 HT may only be used by experienced professionals.

- As pellets broadcast into wet Sikalastic®-8902 or Sika® Concrete Primer on spray applied waterproofing membranes
- As pellets broadcast into wet SikaCor®-HM Mastic
- In hot climate countries and while summer time applications

CHARACTERISTICS / ADVANTAGES

- Allows bond between waterproofing membrane and asphalt overlay
- Hot-melt reaction triggered at $T > +80\text{ °C}$
- Provides mechanical key due to expansion when in contact with hot asphalt
- Development of excellent bond and shear strength

APPROVALS / STANDARDS

- European Technical Approval (ETA) 13/0653 according ETAG 033, as a part of a liquid applied bridge deck waterproofing kit on concrete decks
- BBA/ HAPAS certificate 13/H204 as tack coat system to Sikalastic-841 ST
- BBA/ HAPAS certificate 15/H237 as tack coat system to Sikalastic-851
- Part of the BAST listed system according ZTV-ING, part 7, section 4, as a liquid applied bridge deck waterproofing kit on steel decks

PRODUCT INFORMATION

Composition	Modified Ethyl-Vinyl-Acetate-Copolymer	
Packaging	25 kg bags 750 kg boxes on request	
Appearance / Colour	whitish / yellowish	
Shelf Life	24 month from date of production	
Storage Conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between $+5\text{ °C}$ and $+30\text{ °C}$. Protect from direct sunlight.	
Density	approx. 1.20 kg/l, bulk density Density values determined at $+23\text{ °C}$	(EN ISO 2811-1)
Solid Content	~100 %	

TECHNICAL INFORMATION

Chemical Resistance

Resistant to water, bitumen and de-icing salts

APPLICATION INFORMATION

Consumption

approx. 0.70 kg/m²

Ambient Air Temperature

See related product data sheet of approved tack coat system

APPLICATION INSTRUCTIONS

Broadcast uniformly Sikalastic®-827 HT by hand, low pressure blast equipment or Sika Pellet Distribution Kart.

APPLICATION

Uniformly broadcast Sikalastic®-827 HT by hand, by low pressure blast equipment or by Sika pellet distribution kart.

IMPORTANT CONSIDERATIONS

This product may only be used by experienced professionals.

Sikalastic®-827 HT shall not be broadcasted into the tack coat if pot life of tack coat is exceeded.

In order to develop a proper bond and shear strength, **the temperature of asphalt during rolling (compaction) must not be less than +140 °C** on concrete decks. On steel decks, **the temperature of asphalt during rolling (compaction) must not be less than +160 °C**.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai

Negeri Sembilan D.K., Malaysia

Phone: +606-7991762

Fax: +606-7991980

e-mail: info@my.sika.com

Website: www.sika.com.my



Product Data Sheet
Sikalastic®-827 HT
February 2018, Version 01.01
020702060200000001

Sikalastic-827HT-en-MY-(02-2018)-1-1.pdf