

# PRODUCT DATA SHEET

## Sikament<sup>®</sup> NN MY

### HIGH RANGE WATER-REDUCING CONCRETE ADMIXTURE

#### DESCRIPTION

Formerly known as Sikament<sup>®</sup> NN. Sikament<sup>®</sup> NN MY is a highly effective dual action liquid superplasticiser for the production of free flowing concrete or as a substantial water-reducing agent for promoting high early and ultimate strengths.

Sikament<sup>®</sup> NN MY is chloride free according to BS 5075 and is compatible with all types of Portland Cement including Sulphate Resistant Cement (SRC).

#### USES

Sikament<sup>®</sup> NN MY is used as a superplasticiser in the production of free flowing concrete for:

- Slabs and foundations
- Walls, columns and piers
- Slender components with densely packed reinforcements
- Textured surface finishes

Sikament<sup>®</sup> NN MY is also used as a water-reducing agent leading to high early and ultimate strength concrete for:

- Precast concrete elements
- Prestressed concrete
- Bridges and cantilever structures
- Areas of concrete where formwork must be removed quickly or early loading applied

#### CHARACTERISTICS / ADVANTAGES

As a superplasticiser:

- Workability is greatly improved
- Increased placeability in slender components with packed reinforcements
- Decreases the amount of vibration
- Normal set without retardation
- Significantly reduces the risk of segregation

As a water-reducer:

- Water reduction up to 30 % depending on dosage\*
  - 16 hour compressive strengths increased by up to 100 %\*
  - 28 days strengths improved by up to 40 %\*
- \*(this will depend on dosage and mix design)

#### APPROVALS / STANDARDS

Sikament<sup>®</sup> NN MY conforms to the requirements of ASTM C 494 Type F and BS 8110: Part 1.

#### PRODUCT INFORMATION

<b>Composition</b>	Naphthalene Formaldehyde Sulphonate
<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 208 L drum</li> <li>▪ 1 000 L tank</li> </ul>
<b>Appearance / Colour</b>	Dark brown liquid
<b>Shelf Life</b>	12 months from the date of production

## Storage Conditions

Store properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Keep away from direct sunlight.

## APPLICATION INFORMATION

### Recommended Dosage

Sikament® NN MY can be used at the rate of 600–2 000 ml per 100 kg of cement depending on requirements concerning workability and strength. It is recommended that trial mixes be conducted to determine the exact dosage rate required.

Note: For more specific requirements, advice is available from our Technical Service Department to determine the usage rate for optimum results.

## APPLICATION INSTRUCTIONS

### DISPENSING

Sikament® NN MY shall be dispensed neat into the premixed concrete after all the other concrete components, including total water, have been discharged into the panmixer or truck mixer. Do not dilute Sikament® NN MY.

### BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai  
Negeri Sembilan D.K., Malaysia  
Phone: +606-7991762  
Fax: +606-7991980  
e-mail: info@my.sika.com  
Website: www.sika.com.my



Product Data Sheet  
Sikament® NN MY  
September 2019, Version 01.01  
021302011000001107

SikamentNNMY-en-MY-(09-2019)-1-1.pdf