

## PRODUCT DATA SHEET

# SikaProof®-110 PP-700

Fully bonded, pre-applied organic-inorganic composite membrane for tunnels

### DESCRIPTION

SikaProof®-110 PP-700 consists of a flexible polyolefin (FPO) base layer membrane with a hybrid bonding layer that forms a mechanical and chemical dual bond with the in situ concrete lining, and a non-woven polypropylene geotextile, which is spot-fixed onto the membrane during the manufacturing process and serves as a protection and drainage layer.

### USES

Tunnel waterproofing

### CHARACTERISTICS / ADVANTAGES

- Strong mechanical and chemical bonding properties on inner concrete lining
- No lateral water migration between inner concrete structure and membrane
- Excellent thermal jointing properties
- Highly flexible, also in cold temperatures
- Strong crack bridging ability
- Fast and simple installation

### APPROVALS / STANDARDS

SikaProof®-110 PP-700 is designed and manufactured to meet most international recognised standards. Conforms to KS F 4911 (Waterproofing sheet of synthetic polymer).

### PRODUCT INFORMATION

<b>Composition</b>	Functional layer	Cement filled membrane
	Polymer layer	FPO membrane
	Protection layer	Non-woven polypropylene geotextile
<b>Packaging</b>	SikaProof®-110 PP-700 standard rolls are wrapped individually in a PE-foil. 2.1 m (width) x roll length 20 m or individual as specified.	
<b>Shelf Life</b>	SikaProof®-110 PP-700 membrane rolls have a shelf-life of 36 months from date of production.	
<b>Storage Conditions</b>	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C, Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
<b>Appearance / Colour</b>	Functional layer	Rough / white to grey
	Polymer layer	Smooth / white to grey
	Protection layer	Fleece texture / white
<b>Effective Thickness</b>	1.4 mm (FPO layer 1.0 mm / cement filled layer 0.4 mm) (-5 % / +10 %)	

Mass per Unit Area	2.04 kg/m <sup>2</sup> (including felt)	
Felt Weight	700 g/m <sup>2</sup> (± 10 %)	(EN ISO 9864)

## SYSTEM INFORMATION

System Structure	SikaProof®-11 Anchor SikaProof®-12 Anchor
------------------	--

## TECHNICAL INFORMATION

Resistance to Impact	> 350 mm	(EN 12691)	
Resistance to Static Load	Pass	(EN 12730 (Method B, 24 h / 20 kg))	
Resistance to Static Puncture	> 1.5 kN	(EN ISO 12236)	
Tensile Strength	Machine direction	> 8 N/mm <sup>2</sup>	(EN 12311-2)
	Cross direction	> 8 N/mm <sup>2</sup>	
Elongation	Machine direction	> 500 %	(EN 12311-2)
	Cross direction	> 500 %	
Adhesion in Peel	> 20 N / 50 mm	(EN 1372)	
Resistance to tear (nail shank)	Machine direction	> 500 N	(EN 12310-1)
	Cross direction	> 500 N	
Joint Peel Resistance	Peel resistance of welded seam > 80 N / 50 mm	(EN 12316-2)	
Ambient Maximum Temperature of Liquids	+35 °C max.		
Water Tightness	Pass	(EN 1928 B (24 h / 60 kPa))	
Resistance to lateral water migration	Pass	(ASTM D 5385 mod)	
Water Vapour Transimission	0.4 g/m <sup>2</sup> × 24 hr	(EN 1931 (+23 °C/75% r.h.))	
Durability of Water Tightness against Chemicals	Pass	(EN 1296 (28 d / +23 °C))	(EN 1928 B (24 h / 60 kPa))
		(EN 1296 (28 d / +23 °C))	
Durability of Water Thightness against Ageing	Pass	(EN 1296 (28 d / +23 °C))	(EN 1928 B (24 h / 60 kPa))
		(EN 1296 (28 d / +23 °C))	
Reaction to Fire	E	(EN ISO 11925-2)	

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

Installation works must only be carried out by Sika trained contractors, experienced in the waterproof lining of tunnels and belowground structures. Precaution measures must be taken for installation in wet conditions, at temperatures below +5 °C and when the relative air humidity (RH) is more than 80 %. The effectiveness of these measures must be proven. Fresh air ventilation must always be ensured, espe-

cially when working in closed rooms and in accordance with all relevant local regulations.

The SikaProof®-110 PP-700 is not UV stabilized and cannot be installed on structures permanently exposed to sunlight and weathering.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

## SUBSTRATE QUALITY

The profile of the shotcrete surface must not exceed a ratio of length to depth of 5:1 and its min. radius must be 20 cm. The shotcrete surface must not contain broken aggregates. Any leaks must be sealed with Sika® waterproof plugging mortar, or drained with a Sika® FlexoDrain system. Where necessary to achieve the desired profile/surface, apply a fine sprayed concrete layer on the shotcrete surface with a min. thickness of 3–5 cm and aggregate diameter not exceeding 8 mm.

Steel (girders, reinforcement mesh, anchors, etc.) must also be covered with a minimum of 4 cm fine sprayed concrete. The shotcrete surface must be clean (no loose stones, nails, wires, etc.).

## APPLICATION METHOD / TOOLS

The SikaProof®-110 PP-700 membrane is installed loose laid and mechanically fastened in accordance with the Sika Method Statement for sheet waterproofing membrane installations (available separately on request).

The jointing faces must be dry and free from contaminations. For contaminated / soiled surfaces, follow the instructions for cleaning and preparation etc. in the Sika Method Statement.

All membrane overlaps must be thermally jointed using hand welding gun and pressure rollers or automatic heat welding machines, with individually adjustable and electronically controlled welding temperatures (such as the manual Leister Triac PID / automatic: Leister Twinny S / semi-automatic: Leister Triac Drive). Thermal jointing parameters, such as speed and temperature must be established with trials on site, prior to any thermal jointing works.

T-joints demand specific preparation of the thermal jointing area. In the previously fabricated weld area the overlaps must be chamfered carefully. For more specific instructions refer to the Sika Method Statement.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,  
71800 Nilai, Negeri Sembilan D.K.  
Malaysia  
Phone: +606-7991762  
e-mail: info@my.sika.com  
Website: www.sika.com.my



### Product Data Sheet

SikaProof®-110 PP-700  
September 2023, Version 01.01  
020720301200000005

SikaProof-110PP-700-en-MY-(09-2023)-1-1.pdf