

PRODUCT DATA SHEET

Sika® ViscoCrete® SKY 8705 MY

(formerly MasterGlenium® SKY 8705 (MY))

New generation superplasticising admixture for extended slump retention

DESCRIPTION

Sika® ViscoCrete® SKY 8705 MY is a new generation superplasticiser with super retention technology. It contains polycarboxylate ether polymers and is specially formulated for ready-mix concrete where slump retention, high strength and durability are required in hot climates. The excellent dispersion effect makes Sika® ViscoCrete® SKY 8705 MY the ideal admixture for the ready-mix concrete industry. The ability to work with low water /cement ratios and still obtain extended slump retention allows for the manufacture of high-quality concrete.

Sika® ViscoCrete® SKY 8705 MY is free of chloride and complies with BS EN934 : Part 2 : 2009, and is also compatible with all cements meeting recognised international standards.

USES

- Concrete with less water content than with conventional admixtures
- Faster mixing logistics during large jobs
- High flowability concrete
- Highly durable concrete
- Ready-mixed concrete
- Mass concrete
- Long distance transport
- Pumped concrete
- Hot weather concreting

PRODUCT INFORMATION

Packaging

- 1000 L IBC tank
- Bulk delivery

Shelf Life

12 months from date of production

Storage Conditions

Store at a temperature above 0 °C and in tightly sealed original containers. If frozen, thaw it and completely reconstitute by mild agitation. Do not use compressed air.

CHARACTERISTICS / ADVANTAGES

- High water reduction - High early and ultimate strengths. Low permeability, high durability concrete.
- High flowability - Ease of placing and compaction. No segregation.
- Superior slump retention - No retempering. Ease of delivery to point of placement
- Low shrinkage and creep - Improve dimensional stability. Reduced risk of cracks
- Good cohesion - Ease of pumping. No bleeding.
- Good workability - Excellent surface appearance. Self-compacting concrete
- Minimal bleed water - Excellent concrete quality.
- High elastic modulus - Superior load bearing capacity.

APPLICATION INFORMATION

Recommended Dosage

Dosage of Sika® ViscoCrete® SKY 8705 MY depends on the mix design, ambient conditions and degree of water reduction and workability required. Sika® ViscoCrete® SKY 8705 MY is dispensed at a rate of 870 ml to 1500 ml per 100 kg of cementitious material. Other dosages may also be used depending on the specific working conditions. Trial mixes should be made with job materials to determine the optimum dosage required for a specified job requirement.

Dispensing

Sika® ViscoCrete® SKY 8705 MY is a ready-to-use admixture to be added to the concrete mix as a separate component. Optimal mixing water reduction is obtained if Sika® ViscoCrete® SKY 8705 MY is poured into the concrete mix right after the addition of the first 50–70 % of the mixing water. Avoid adding the admixture to the dry aggregates. A separate dispenser and feed line must be used.

SYSTEM INFORMATION

Compatibility

Sika® ViscoCrete® SKY 8705 MY can be used in combination with other Sika® ViscoCrete® and SikaPlast® admixtures to achieve longer slump retention or other specific working requirements. The dosage employed in such cases may be different from the above recommendation. Trial mixes should be made with job materials to determine the optimum dosage required for a specified job requirement.

Sika® ViscoCrete® SKY 8705 MY is not compatible with Sikament® RB admixtures.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,
71800 Nilai, Negeri Sembilan D.K.
Malaysia
Phone: +606-7991762
e-mail: info@my.sika.com
Website: www.sika.com.my



Product Data Sheet
Sika® ViscoCrete® SKY 8705 MY
October 2024, Version 01.02
021301011000005681

SikaViscoCreteSKY8705MY-en-MY-(10-2024)-1-2.pdf

