

SYSTEM DATA SHEET

Sikafloor® MultiDur ET-31 ECF/V

TEXTURED, ELECTROSTATICALLY CONDUCTIVE, CHEMICALLY RESISTANT EPOXY COATING FOR VERTICAL SURFACES

DESCRIPTION

Sikafloor® MultiDur ET-31 ECF/V is a two part, textured, electrostatic conductive, coloured epoxy coating system with very high chemical resistance. "Total solid epoxy composition acc. to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)".

USES

Sikafloor® MultiDur ET-31 ECF/V may only be used by experienced professionals.

It is used as:

- Chemically highly resistant epoxy coating for vertical surfaces in concrete and screed surfaces in bund areas for the protection against water contaminating liquids (contact Sika technical service for specific information)
- Electrostatically conductive epoxy coating for vertical surfaces subject to chemical and mechanical exposure in production and storage facilities

CHARACTERISTICS / ADVANTAGES


- Very high chemical resistance
- High mechanical resistance
- Impervious to liquids
- Abrasion resistant
- Electrostatically conductive
- Good sag resistance

PRODUCT INFORMATION

Packaging	Please refer to individual Product Data Sheet.	
Shelf Life	Please refer to individual Product Data Sheet.	
Storage Conditions	Please refer to individual Product Data Sheet.	

SYSTEM INFORMATION

System Structure



1. Primer	Sikafloor®-161 HC
2. Conductive undercoat + Earthing	Sikafloor®-381 ECF filled with
connection	2.5-4.0 % Extender T + Sika® Earth-
	ing Kit
3. Conductive primer	Sikafloor®-220 W Conductive
4. Final conductive coating	Sikafloor®-381 ECF filled with
	2 5–4 0 % Extender T

The system configurations as described must be fully complied with and may not be changed.

Composition	Ероху	
Appearance	Orange peel textured, semi-gloss	
Colour	Almost unlimited choice of colour shades. Due to the nature of carbon fibres providing the conductivity, it is not possible to achieve exact colour matching. With very bright colours (such as yellow and orange), this effect is increased. Under direct sun light there may be some variations and colour variation, this has no influence on the function and performance of the coating.	

Nominal Thickness ~ 1.5 mm

TECHNICAL INFORMATION

Electrostatic Behaviour	Resistance to ground ¹	$R_g < 10^9 \Omega$	(IEC 61340-4-1)
	Typical average resistance to ground ²	$R_g < 10^6 \Omega$	(DIN EN 1081)

 $^{^1\,}$ In accordance with IEC 61340-5-1 and ANSI/ESD S20.20. $^2\,$ Readings may vary, depending on ambient conditions (i.e. temperature, humidity) and measurement equipment.



APPLICATION INFORMATION

Coating	Product	Consumption			
Primer	Sikafloor®-161 HC	1-2 x ~ 0.3-0.5 kg/m ²			
Scratch coat (if required)	Sikafloor®-161 HC	Refer to PDS of Sika- floor®-161 HC			
Conductive undercoa	Sikafloor®-381 ECF filled with 2.5–4.0 % Extender T	1 x 1.25 kg/m²			
Earthing connection	Sika® Earthing Kit	1 earthing point per approx. 200–300 m², min. 2 per room.			
Conductive primer	Sikafloor®-220 W Co ductive	n- 1 x 0.08–0.10 kg/m²			
Final conductive coat ing	- Sikafloor®-381 ECF filled with 2.5–4.0 % Extender T	1 x 1.25 kg/m²			
	These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.				
+10 °C min. / +30 °C ı	nax.				
80 % r.h. max.					
The substrate and un	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.				
+10 °C min. / +30 °C r	+10 °C min. / +30 °C max.				
< 1 % nhw maisture c	<4 % pbw moisture content. Test method: Sika Tramex Meter, CM-measurement or Oven-Dry-Method. No rising moisture according to ASTM (Polyethylene-sheet).				
Test method: Sika Tra	mex Meter, CM-measur				
Test method: Sika Tra No rising moisture ac Before applying Sikaf	mex Meter, CM-measur cording to ASTM (Polyetl oor®-381 ECF on Sikafloo	hylene-sheet). or®-161 HC allow:			
Test method: Sika Tra No rising moisture ac	mex Meter, CM-measur cording to ASTM (Polyetl oor®-381 ECF on Sikafloo	hylene-sheet). or®-161 HC allow: Maximum			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu	mex Meter, CM-measur cording to ASTM (Polyet oor®-381 ECF on Sikafloo re Minimum	hylene-sheet). or®-161 HC allow: Maximum 4 days			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu +10 °C	mex Meter, CM-measur cording to ASTM (Polyetl oor®-381 ECF on Sikafloo re Minimum 24 hours	hylene-sheet). or®-161 HC allow: Maximum			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu +10 °C +20 °C +30 °C Before applying Sikaf	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon re Minimum 24 hours 12 hours 8 hours	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperatu	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon re Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperatu +10 °C	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon re Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum 48 hours	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum 3 days			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperatu +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperatu	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon re Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon re Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum 48 hours 24 hours 12 hours	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum 3 days 2 days 1 days 1 days or®-220 W Conductive allow			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloon Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum 48 hours 24 hours 12 hours 10 hours Minimum Minimum Minimum Minimum Minimum	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum 3 days 2 days 1 days 1 days or®-220 W Conductive allow Maximum Maximum			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloor Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive Minimum 48 hours 24 hours 12 hours 10 hours 10 hours 10 hours	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum 3 days 2 days 1 days or®-220 W Conductive allow Maximum 7 days			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C Before applying Sikaf Substrate temperature +10 °C +20 °C	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloo re Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum 48 hours 24 hours 12 hours 10 hours 10 hours 11 hours 12 hours	hylene-sheet). or®-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor®-381 ECF allow Maximum 3 days 2 days 1 days or®-220 W Conductive allow Maximum 7 days 5 days 5 days			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Times are approxima	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloor Performance 24 hours 12 hours 8 hours oor®-220 W Conductive Performance 48 hours 12 hours 12 hours 12 hours 12 hours 13 hours 14 hours 15 hours 16 hours 17 hours 18 hours 19 hours 19 hours 19 hours 19 hours 10 hours 11 hours	hylene-sheet). or*-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor*-381 ECF allow Maximum 3 days 2 days 1 days or*-220 W Conductive allow Maximum 7 days 5 days 4 days y changing ambient condi-			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Times are approximations particularly tem	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloor Parameter Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive Parameter Minimum 48 hours 12 hours 12 hours oor®-381 ECF on Sikafloor Parameter Minimum 26 hours 17 hours 12 hours te and will be affected by perature and relative hu	hylene-sheet). or*-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor*-381 ECF allow: Maximum 3 days 2 days 1 days or*-220 W Conductive allow: Maximum 7 days 5 days 4 days y changing ambient condimidity.			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Times are approximations particularly tem Temperature For	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloor Minimum 24 hours 12 hours 8 hours oor®-220 W Conductive Minimum 48 hours 24 hours 12 hours 10 hours 10 hours 11 hours 12 hours 12 hours 12 hours 13 hours 14 hours 15 hours 16 hours 17 hours 18 hours 19 hours 19 hours 19 hours 10 hours 11 hours 12 hours	hylene-sheet). or*-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor*-381 ECF allow: Maximum 3 days 2 days 1 days 1 days or*-220 W Conductive allow: Maximum 7 days 5 days 4 days y changing ambient condimidity. affic Full cure			
Test method: Sika Tra No rising moisture ac Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Before applying Sikaf Substrate temperature +10 °C +20 °C +30 °C Times are approximations particularly tem Temperature +10 °C	mex Meter, CM-measur cording to ASTM (Polyet) oor®-381 ECF on Sikafloor 24 hours 12 hours 8 hours oor®-220 W Conductive re Minimum 48 hours 24 hours 12 hours 10 hours 12 hours 12 hours 12 hours 12 hours 13 hours 14 hours 15 hours 16 hours 17 hours 18 and will be affected by perature and relative hu oot traffic Light tra	hylene-sheet). or*-161 HC allow: Maximum 4 days 2 days 1 days on Sikafloor*-381 ECF allow: Maximum 3 days 2 days 1 days or*-220 W Conductive allow: Maximum 7 days 5 days 4 days 4 days y changing ambient condimidity. affic Full cure ~ 10 days			
	Primer Scratch coat (if required) Conductive undercoa Earthing connection Conductive primer Final conductive coating These figures are the due to surface porosite porosite to surface porosite porosite porosite porosite porosite porosite porosite porosite porosit	Primer Scratch coat (if required) Conductive undercoat Earthing connection Conductive primer Earthing connection Sikafloor®-381 ECF filled with 2.5–4.0 % Extender T Sika® Earthing Kit Conductive primer Sikafloor®-381 ECF filled with 2.5–4.0 % Extender T Sika® Earthing Kit Sikafloor®-220 W Conductive Sikafloor®-381 ECF filled with 2.5–4.0 % Extender T These figures are theoretical and do not allow due to surface porosity, surface profile, variated to surface profile, var			



FURTHER DOCUMENTS

Please refer to:

- Sika® Method Statement Mixing and Application of Flooring Systems
- Sika® Method Statement Surface Evaluation & Preparation

IMPORTANT CONSIDERATIONS

- Due to the nature of carbon fibres providing the conductivity, surface irregularities might be possible.
 This has no influence on the function and performance of the coating.
- Do not apply the Sikafloor® MultiDur ET-31 ECF/V system on substrates in which significant vapour pressure may occur.
- Do not blind the primer.
- The freshly applied final conductive coating of the Sikafloor® MultiDur ET-31 ECF/V system must be protected from damp, condensation and water for at least 24 hours.
- Only start application of Sikafloor® conductive primer after the priming coat has dried tack-free all over.
 Otherwise there is a risk of wrinkling or impairing of the conductive properties.
- Under certain conditions, underfloor heating combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking - reducing or breaking conductivity.
- For exact colour matching, ensure the final conductive coating of the Sikafloor® MultiDur ET-31 ECF/V system in each area is applied from the same control batch numbers.
- Please note, that measuring results of the orange peel textured Sikafloor® MultiDur ET-31 ECF/V system may vary due to a difference in surface profile.
- The test person, ambient conditions, measurement equipment, cleanliness of the floor have a substantial influence on the measurement results.

All measurement values for the Sikafloor® MultiDur ET-31 ECF/V system stated in the system data sheet (apart from the ones referring to proof statements) were measured under the following conditions:

Ambient conditions:	+23 °C/50%
Measurement device for	Metriso 2000 (Warmbier)
the Resistance to Ground:	or comparable
Surface resistance probe:	Tripod electrode acc.
•	DIN EN 1081

The number of conductivity measurements is strongly recommended to be as shown in the table below:

Ready applied area	Number of measure- ments
< 10 m ²	6 measurements
< 100 m ²	10–20 measurements
<1000 m ²	50 measurements

<5000 m²

100 measurements

In case of values lower/higher as required, additional measurements has to be carried out, approx. 30 cm around the point with insufficient readings. If the newly measured values are in accordance with the requirements, the total area is acceptable. Installation of earthing points: Please refer to the Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

Numbers of earth connections: Per room at least 2 earthing points. The optimum number of earth connections depends on the local conditions and should be specified using available drawings.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai Negeri Sembilan D.K., Malaysia Phone: +606-7991762 Fax: +606-7991980 e-mail: info@my.sika.com Website: www.sika.com.my





SYSTEM DATA SHEET Sikafloor® MultiDur ET-31 ECF/V August 2017, Version 01.01 02081190000000034 SikafloorMultiDurET-31ECFV-en-MY-(08-2017)-1-1.pdf

