

## PRODUCT DATA SHEET

# SikaFume® SF 3263 MY

Silicafume mineral additive in slurry form

### DESCRIPTION

SikaFume® SF 3263 MY is a modified concrete additive in liquid form based on Sika® Silica Fume Technology. It is a formulated blend of highly reactive pozzolanic materials and stabilisers designed to produce high quality concrete. SikaFume® SF 3263 MY is particularly suitable for chemical resistance, exposure to aggressive atmospheres, abrasion and high strength mixes (in excess of 80 N/mm<sup>2</sup>). It should always be used in conjunction with a superplasticiser from the Sika range.

### USES

- Concrete exposed to aggressive liquids:
  - Farm and food processing industries: silos, floors etc.
  - Chemical industries: floors, chemical fertiliser storage etc.
  - Service Stations: oils, fuels, washing areas etc.
  - Sewage treatment plants: structures, sewers, etc.
  - Foundations: waterproofing structures etc.
  - Sprayed concrete applications
- Concrete exposed to aggressive atmospheres:
  - Marine constructions
- Concrete exposed to air pollution (urban and industrial areas)
- Concrete exposed to erosion and abrasion:
  - Construction of culverts – dams – concrete subject to heavy traffic or wear and tear

### CHARACTERISTICS / ADVANTAGES

SikaFume® SF 3263 MY improves properties of the fresh concrete, such as cohesion, bond and water efficiency. In hardened concrete the highly active pozzolanic material reacts with the free lime produced by the hydration of the cement to improve strength, density and durability of the concrete.

SikaFume® SF 3263 MY will provide the following benefits:

- Enhanced rheology
- Increased early strength
- Increased final strength
- Increased impermeability to liquids
- Increased impermeability to gases
- Reduced chloride penetration
- Reduced alkali silica reaction in aggregates
- Increased resistance to freeze/thaw cycle
- Increased resistance to acids
- Increased resistance to abrasion

### PRODUCT INFORMATION

<b>Composition</b>	Slurry of (50 ± 1.5) % silica fume
<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 1000 L IBC tank</li> <li>▪ Bulk delivery</li> </ul>
<b>Appearance / Colour</b>	Grey slurry
<b>Shelf Life</b>	3 months from date of delivery, given correct storage of material. Material must be fully stirred / agitated on a regular basis during use.
<b>Storage Conditions</b>	Store in closed containers to prevent contamination, stir / agitate regularly

and protect from frost. For best results refer to SikaFume® SF 3263 MY Storage and Dispensing Guide, available separately.

---

Density	1.35–1.45 kg/l at 25 °C
---------	-------------------------

---

pH-Value	7.5–10.0
----------	----------

---

## TECHNICAL INFORMATION

---

Concreting Guidance	Concrete with SikaFume® SF 3263 MY will be subject to reduced bleed and as such vulnerable to surface water loss. Proper curing is essential.
---------------------	---

---

Concrete Mixing Time	SikaFume® SF 3263 MY may require additional mixing time depending upon the efficiency of the mixer used.
----------------------	--

---

## SYSTEM INFORMATION

---

Compatibility	SikaFume® SF 3263 MY is compatible with other Sika® admixtures, trials are recommended to ascertain optimum dosage. Please contact Sika technical services for more information.
---------------	--

---

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### DISPENSING

The addition rate of SikaFume® SF 3263 MY is generally between 10 % and 20 % by weight of cement. Contact Sika technical services for detailed advice on the dosage requirements.

SikaFume® SF 3263 MY should be added with the mixing water. Ensure no settlement of the SikaFume® SF 3263 MY has occurred during storage, thoroughly re-mix if required. Due to material density and solids content, specialist pumps are recommended for dispensing, contact your local Sika representative for additional information.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.  
Lot 689, Nilai Industrial Estate,  
71800 Nilai, Negeri Sembilan D.K.  
Malaysia  
Phone: +606-7991762  
e-mail: info@my.sika.com  
Website: www.sika.com.my



Product Data Sheet  
SikaFume® SF 3263 MY  
March 2026, Version 01.01  
021403031000000140

SikaFumeSF3263MY-en-MY-(03-2026)-1-1.pdf

